

PHASE IV MONUMENT RESTORATION  
RANDOLPH CEMETERY  
Columbia, S.C.

Final Assessment and Treatment Documentation  
For Restoration Work Completed by

Jonathan Appell  
Gravestone Conservator  
West Hartford, CT

For the Committee for the Restoration and  
Beautification of Randolph Cemetery

GRANT FUNDING PROVIDED BY:

Richland County Conservation Commission

May 2013

## Randolph Cemetery Gravestone Preservation Project

The entire Phase IV gravestone preservation project has been fully completed. All of the documentation is included, which contains an individual stone assessment form, and the related before and after photos, for each of the 43 gravestones and monuments, which were conserved in this project. Two DVD disks contain all of the photographs taken before, during and after the project was completed. They are also included here along with this overview. Some of the original photographs taken before the project was performed, included fragments only or pieces of other stones already on the list. Additional stones in need or conservation were selected, in place of these extra photos.

There was only one gravestone on the original list that was not able to be re-set upright into a vertical position. This was due to a great deal of missing stone and extensive erosion to the marble. It was instead re-set on the flat, on a bed of gravel to allow for evaporation, to make it readable and to safely enable the mowers to ride over it, without inflicting additional damage. Overall the cemetery must have had a great deal of previous modification, theft, and vandalism in some historical time periods. This is based on the large number of missing bases, and or missing headstones, and or the associated missing and broken portions of monumental elements.

All of the gravestones and monuments conserved were thoroughly cleaned with the stone cleaner D2. The stones that had been fallen for a long period of time have deeply seated staining associated with mineral deposits, primarily from the element iron in the soil. These stones will continue to become cleaner over time, from UV in the form of sunlight, as well as washing in future rain events.

### WORKSHOP

A one-day workshop was held on April 13, 2013 and led by the conservator on this project, Jonathan Appell. There were sixteen attendees, with several traveling into town from Fairfield County and Summerville, South Carolina. Three committee members for CRBRC were also present. Participants got to clean headstones and work with resetting fallen and buried stones, and learned about epoxy and mortar repairs. This workshop was included as part of the Phase IV Restoration and grant funds.

**Table of Projects Sites Completed During Phase IV Restoration**

#	Identification	Page
1	61.01: Lucius Wimbush, Reconstruction Era Senator	88
2*	202: Thomas W. Keitt	42
3	124.02: Eliza D. Cleckley	14
4	930: Willie Wilkins	86
5	929: Unknown previously, Marcia M.Meyers, d. 1901	56
6*	949: Sarah Stevenson	72
7	111: James Daniels	36
8	112.03: Charles M. Wilder, Reconstruction Era	10

	Legislator, Post Master	
9	134: Holland Mitchell	30
10	437.21: Unknown (parts of stones)	
11	437.20: Maggie Logan	54
12	437.16: Robert Richardson	66
13	437.15: J.L. Simons, Jr.	34
14	437.02: Josie	40
15	437.03: Unknown (parts of stones)	
16	437.04: Unknown (parts of stones)	
17	437.05: A.E.F, W&S.B. (parts of stones)	
18	437.06: Sarah Agnes Brown	70
19	437.07: Tom Simons	82
20	437.08: Unknown (parts of stones)	
21	437.09: Unknown (parts of stones)	
22	437.12: Unknown (parts of stones)	
23	401: Unknown	4
24*	418: Unknown, S.M.P., Susan M. Pearson, d. 1893	78
25	427: Unknown previously, Martha Brown, d. 1923	58
26*	439: Maggie Brown	52
27*	467: Unknown previously, Vencson Young, d. 1900	84
28	471: Unknown previously, Ester Alexander	24
29	555: John Nesbit	38
30	570: Unknown previously, Edward Gadsden, d. 1926	18
31	905: Thomas Bacon	80
32	908: Sallie Mack	68
33	916: Ben Davis	8
34	926: Unknown previously, Elizabeth Howell, d. 1921	20
35	952: Unknown previously, David D. Anderson, d. 1961	16
36	983: Unknown previously, Elizabeth Patterson	22
37	550.01: Lapoleon Green	44
Extra	Annie Bacon	6
Extra	Clarence Henderson	12
Extra	Elizabeth Patterson, d. 1906	22
Extra	Fannie Clifton, d. 1926	26
Extra	Hanah Picket	28
Extra	J.H. Bolick, d. 1913	32
Extra	Lenora Caughman	46
Extra	Lydia Wilder	48
Extra	Mrs. M.L. Cayce	50
Extra	Martha Cannon, d. 1918	60
Extra	Merrit Davaul, d. 1915	62
Extra	Rev. I.N. Nesbit, d. 1917	64
Extra	Simons family monument	74
Extra	Susan Brown	76

PAGE LEFT BLANK

**Interred:** Unknown  
\*Number 23

**Death Date:** Unknown. “Age 72 erected  
by their children”

**Location:** 401

**Marker Type:** Tablet stone on base

**Material:** Concrete

**Condition:** Tablet fractured in three pieces /  
missing top

---

### Cleaning:

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### Mends:

Join the fragments with Akemi, Akepox 2030. Immediately remove any adhesive which has spread to the outer surface of the marker.

### Fills:

Clean surfaces to be built up as described above. Infill lost stone with Jahn’s Restoration Mortar, or St. Astier Lithomex. Follow the manufacturer guidelines for application. Pre-wet marker, apply a scratch coat, build up as needed. Cut down mortar once hardened enough to not stick to cutting edge. Mist down 3 times per day for three days.

---

### Treatment Notes:

Raise and re-level base. Join fractured tablet with stone epoxy. Infill voids. Clean with D2, re-grade and seed. Entire top section including name missing.

### Treatment Personal:

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Annie Bacon

**Death Date:** 1914

**Location:** Extra stone, not on list  
Next to Thomas Bacon

**Marker Type:** Tablet stone

**Material:** Marble

**Condition:** Tablet fractured, only top portion  
found off site

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Marker found on completely different plot. Base and lower portion of tablet missing. Procure similar size base from junk pile. Enlarge socket to fit tablet. Saw bottom of tablet off square. Set base on sand and gravel. Reset in historic pointing mortar. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Ben Davis

**Death Date:** 1926

**Location:** 916

**Marker Type:** Veterans tablet stone

**Material:** Marble

**Condition:** Leaning and too high, biological growth

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Excavate and remove stone from ground. Reset into sand and gravel to proper height. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Charles M. Wilder

**Death Date:** 1902

**Location:** 112.03

**Marker Type:** Large three piece monument

**Material:** Granite

**Condition:** Leaning forward / misaligned  
from base

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Re-level entire monument by levering and packing sand and gravel under base. Raise headstone onto blocks. Remove old joining material. Reset with stone epoxy, lead wedges, and monument setting compound. Re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Clarence H. Henderson

**Death Date:** 1828

**Location:** Extra stone, not on list  
Next to Keitt

**Marker Type:** Slanted tablet

**Material:** Concrete

**Condition:** Fallen

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Marker found fallen next to Keitt. Set in sand and gravel. In line where found. Raise and re-level base. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Eliza D. Cleckley

**Death Date:** 1910

**Location:** 124.02

**Marker Type:** Marble monument / two bases

**Material:** Marble

**Condition:** Severely leaning

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

None required

### **Fills:**

None required

---

### **Treatment Notes:**

Very badly leaning forward. Hanging on pins. Deconstruct monument using lifting tripod. Excavate and re-level lower base. Join bases, and headstone employing internal stone epoxy, lead spacers, and monument setting compound. Re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** David D. Anderson

**Death Date:** 1961

**Location:** 952

**Marker Type:** Veteran stone

**Material:** Marble

**Condition:** Tablet fractured in two pieces

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Join the fragments with Akemi, Akepox 2030. Immediately remove any adhesive which has spread to the outer surface of the marker.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Fractures in two and fallen face down. Join fractured tablet with stone epoxy. Reset in sand and gravel. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Edward Gadsden

**Death Date:** 1926

**Location:** 570

**Marker Type:** Veteran stone

**Material:** Marble

**Condition:** Tablet fractured in two pieces

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Join the fragments with Akemi, Akepox 2030. Immediately remove any adhesive which has spread to the outer surface of the marker.

### **Fills:**

Clean surfaces to be built up as described above. Infill lost stone with Jahn's Restoration Mortar, or St. Astier Lithomex. Follow the manufacturer guidelines for application. Pre-wet marker, apply a scratch coat, build up as needed. Cut down mortar once hardened enough to not stick to cutting edge. Mist down 3 times per day for three days.

---

### **Treatment Notes:**

Only very top of stone visible. Fractured in two pieces, almost completely buried. Join fractured tablet with stone epoxy. Infill large void areas. Reset in sand and gravel upright. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Elizabeth Howell

**Death Date:** 1921

**Location:** 926

**Marker Type:** Tablet stone in socket base

**Material:** Marble

**Condition:** Tablet fractured in two pieces,  
fallen face down

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Join the fragments with Akemi, Akepox 2030. Immediately remove any adhesive which has spread to the outer surface of the marker.

### **Fills:**

Clean surfaces to be built up as described above. Infill lost stone with Jahn's Restoration Mortar, or St. Astier Lithomex. Follow the manufacturer guidelines for application. Pre-wet marker, apply a scratch coat, build up as needed. Cut down mortar once hardened enough to not stick to cutting edge. Mist down 3 times per day for three days.

---

### **Treatment Notes:**

Lift and move base. Excavate and lower to proper height. Reset base on sand and gravel. Join fractured tablet with stone epoxy. Infill void areas. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interned:** Elizabeth Patterson

**Death Date:** 1906

**Location:** 983

**Marker Type:** Tablet stone in socket base

**Material:** Marble

**Condition:** Tablet fractured in two pieces and buried underground

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Join the fragments with Akemi, Akepox 2030. Immediately remove any adhesive which has spread to the outer surface of the marker.

### **Fills:**

Clean surfaces to be built up as described above. Infill lost stone with Jahn's Restoration Mortar, or St. Astier Lithomex. Follow the manufacturer guidelines for application. Pre-wet marker, apply a scratch coat, build up as needed. Cut down mortar once hardened enough to not stick to cutting edge. Mist down 3 times per day for three days.

---

### **Treatment Notes:**

Raise and re-level base. Excavate and unearthen buried fractured tablet. Join fractured tablet with stone epoxy. Infill large void areas. Reset in historic pointing mortar. Clean with D2, re-grade and seed. Unlettered tablet found under base.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Ester Alexander

**Death Date:** Unknown

**Location:** 471

**Marker Type:** Tablet stone in socket base

**Material:** Marble

**Condition:** Tablet fractured in multiple pieces  
very highly eroded, unable to repair

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not possible.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Tablet fallen and partially buried. Very high level of deterioration with large pieces missing. Unable to repair to stand vertically. Excavate and install gravel pad to lay stone on. Reset flat with grade so mowers do not hit. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Fannie Clifton

**Death Date:** 1926

**Location:** Extra stone, not on list

**Marker Type:** Rounded front, marble slant

**Material:** Marble

**Condition:** Tipped over

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Raise and re-level marker on sand and gravel. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Hanah Picket

**Death Date:** Unknown

**Location:** Extra stone, not on list

**Marker Type:** Tablet stone on cement base

**Material:** Cement

**Condition:** Leaning and biological growth

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Raise and realign in row. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Holland Mitchell

**Death Date:** 1890

**Location:** 134

**Marker Type:** Tablet stone in socket base

**Material:** Marble

**Condition:** Fractured into three pieces / broken off in base

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Join the fragments with Akemi, Akepox 2030. Immediately remove any adhesive which has spread to the outer surface of the marker.

### **Fills:**

Clean surfaces to be built up as described above. Infill lost stone with Jahn's Restoration Mortar, or St. Astier Lithomex. Follow the manufacturer guidelines for application. Pre-wet marker, apply a scratch coat, build up as needed. Cut down mortar once hardened enough to not stick to cutting edge. Mist down 3 times per day for three days.

---

### **Treatment Notes:**

Raise and re-level base. Chisel out broken tablet in base. Enlarge socket so tablet fits into base. Join fractured tablet with stone epoxy. Infill large void areas. Reset in historic pointing mortar. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** J.H. Bolick

**Death Date:** 1913

**Location:** Extra stone, not on list

**Marker Type:** Tablet stone in socket base

**Material:** Marble

**Condition:** Tablet fractured in two pieces

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Join the fragments with Akemi, Akepox 2030. Immediately remove any adhesive which has spread to the outer surface of the marker.

### **Fills:**

Clean surfaces to be built up as described above. Infill lost stone with Jahn's Restoration Mortar, or St. Astier Lithomex. Follow the manufacturer guidelines for application. Pre-wet marker, apply a scratch coat, build up as needed. Cut down mortar once hardened enough to not stick to cutting edge. Mist down 3 times per day for three days.

---

### **Treatment Notes:**

Raise and re-level base. Join fractured tablet with stone epoxy. Infill void areas. Reset in historic pointing mortar. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** J.L. Simons, Jr.

**Death Date:** 1915

**Location:** 437.15

**Marker Type:** Tablet stone in socket base

**Material:** Marble

**Condition:** Tablet fractured in two pieces

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Join the fragments with Akemi, Akepox 2030. Immediately remove any adhesive which has spread to the outer surface of the marker.

### **Fills:**

Clean surfaces to be built up as described above. Infill lost stone with Jahn's Restoration Mortar, or St. Astier Lithomex. Follow the manufacturer guidelines for application. Pre-wet marker, apply a scratch coat, build up as needed. Cut down mortar once hardened enough to not stick to cutting edge. Mist down 3 times per day for three days.

---

### **Treatment Notes:**

Raise and re-level base. Join fractured tablet with stone epoxy. Infill large void areas. Reset in historic pointing mortar. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** James Daniels

**Death Date:** 1922

**Location:** 111

**Marker Type:** Veterans tablet stone

**Material:** Marble

**Condition:** Leaning / too high

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Veterans tablet either set too high or heaved above proper height. Excavate and remove from ground. Reset lowered at proper height. Pack sand and gravel around stone. Re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** John Nesbit

**Death Date:** 1928

**Location:** 555

**Marker Type:** Tablet stone on socket base

**Material:** Concrete

**Condition:** Tablet fractured in two pieces

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Join the fragments with Akemi, Akepox 2030. Immediately remove any adhesive which has spread to the outer surface of the marker.

### **Fills:**

Clean surfaces to be built up as described above. Infill lost stone with Jahn's Restoration Mortar, or St. Astier Lithomex. Follow the manufacturer guidelines for application. Pre-wet marker, apply a scratch coat, build up as needed. Cut down mortar once hardened enough to not stick to cutting edge. Mist down 3 times per day for three days.

---

### **Treatment Notes:**

Tablet fractures, fallen and partially buried. Raise and re-level base. Join fractured tablet with stone epoxy. Infill large void areas. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Josie

**Death Date:** 1873

**Location:** 437.02

**Marker Type:** Tablet stone in socket base

**Material:** Marble

**Condition:** Tablet separate from base buried  
in dirt

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Base found in corner of plot. Set base on sand and gravel at end of row. Reset in historic pointing mortar. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Thomas W. Keitt

**Death Date:** 1897

**Interred:** Alice Keitt

**Death Date:** 1922

**Location:** 202

**Marker Type:** Tablet stone on two bases

**Material:** Concrete

**Condition:** Tablet broken in half, base leaning

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Join the fragments with Akemi, Akepox 2030. Immediately remove any adhesive which has spread to the outer surface of the marker.

### **Fills:**

Clean surfaces to be built up as described above. Infill lost stone with Jahn's Restoration Mortar, or St. Astier Lithomex. Follow the manufacturer guidelines for application. Pre-wet marker, apply a scratch coat, build up as needed. Cut down mortar once hardened enough to not stick to cutting edge. Mist down 3 times per day for three days.

---

### **Treatment Notes:**

Excavate, realign and level base with sand and gravel. Clean and join fragments. Infill loss, clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Laura Lapoleon Green

**Death Date:** 1961

**Location:** 550.01

**Marker Type:** Slant marker on base

**Material:** Granite

**Condition:** Off base, on adjacent rock

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Slant located off base. Raise, realign and level base. Chisel off old joining material. Join slant to base with stone epoxy, lead wedges and monument setting compound. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Lenora Caughman

**Death Date:** 1918

**Location:** Extra stone, not on list

**Marker Type:** Head stone on base

**Material:** Marble

**Condition:** Leaning, unstable

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Remove head stone off base. Remove old bonding material. Re-level base. Join together with stone epoxy lead wedges and monument setting compound. Additionally join fractured cast vase. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Lydia Wilder

**Death Date:** 1890

**Location:** Extra stone, not on list

**Marker Type:** Tablet stone on two bases

**Material:** Marble

**Condition:** Leaning and unstable

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.


---

### **Treatment Notes:**

Raise and re-level base. Lift head stone off of base. Remove old bonding material. Join with monument setting compound, lead wedges and stone epoxy. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Mrs. M.L. Cayce

**Death Date:** Unknown

**Location:** Extra stone, not on list

**Marker Type:** Tablet stone

**Material:** Marble

**Condition:** Badly leaning forward

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Excavate and remove from ground. Reset with sand and gravel. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Maggie Brown

**Death Date:** Unknown

**Location:** 439

**Marker Type:** Tablet stone in concrete

**Material:** Concrete

**Condition:** Fallen backward

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Raise and re-level base. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Maggie Logan

**Death Date:** 1889

**Location:** 437.20

**Marker Type:** Tablet stone, socket base

\*Number 10, plot 437.21, does not exist and is part of this stone.

\*\*Cross is part of a different stone with undetermined location

**Material:** Marble

**Condition:** Broken, fractured out of base

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Join the fragments with Akemi, Akepox 2030. Immediately remove any adhesive which has spread to the outer surface of the marker.

### **Fills:**

Clean surfaces to be built up as described above. Infill lost stone with Jahn's Restoration Mortar, or St. Astier Lithomex. Follow the manufacturer guidelines for application. Pre-wet marker, apply a scratch coat, build up as needed. Cut down mortar once hardened enough to not stick to cutting edge. Mist down 3 times per day for three days.


---

### **Treatment Notes:**

Fractured pieces found scattered behind base. Raise and re-level base. Enlarge socket so tablet fits into base. Join fractured tablet with stone epoxy. Infill large void areas. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Marcia M. Meyers

**Death Date:** 1901

**Location:** 929

**Marker Type:** Tablet stone

**Material:** Marble

**Condition:** Missing base / leaning on tree

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Tablet stone found leaning against tree. No associated base found. Cast new socket base to the right of Willie Wilkins. Set into socket base with historic pointing mortar. Re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Martha Brown

**Death Date:** 1923

**Location:** 427

**Marker Type:** Tablet stone on socket base

**Material:** Concrete

**Condition:** Fallen forward

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Raise and re-level base and tablet stone. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Martha Cannon

**Death Date:** 1918

**Location:** Extra stone, not on list

**Marker Type:** Small pillar monument w/  
earn on two bases

**Material:** Marble

**Condition:** Only top of base visible near road

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.


---

### **Treatment Notes:**

Excavate and raise base. Very badly sunken. Upper base pillar monument and earn found underground. Clean and reconstruct monument. Join with monument setting compound lead wedges and stone epoxy. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Merrit Davaul

**Death Date:** 1915

**Location:** Extra stone, not on list

**Marker Type:** Tablet stone in socket base

**Material:** Marble

**Condition:** Tablet fractured in two pieces  
and upper portion buried

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Join the fragments with Akemi, Akepox 2030. Immediately remove any adhesive which has spread to the outer surface of the marker.

### **Fills:**

Clean surfaces to be built up as described above. Infill lost stone with Jahn's Restoration Mortar, or St. Astier Lithomex. Follow the manufacturer guidelines for application. Pre-wet marker, apply a scratch coat, build up as needed. Cut down mortar once hardened enough to not stick to cutting edge. Mist down 3 times per day for three days.


---

### **Treatment Notes:**

Raise and re-level base. Join fractured tablet with stone epoxy. Infill void areas. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Rev. I.N. Nesbit

**Death Date:** 1917

**Location:** Extra stone, not on list

**Marker Type:** Head stone on base

**Material:** Marble

**Condition:** Detached and unstable

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Clean surfaces to be built up as described above. Infill lost stone with Jahn's Restoration Mortar, or St. Astier Lithomex. Follow the manufacturer guidelines for application. Pre-wet marker, apply a scratch coat, build up as needed. Cut down mortar once hardened enough to not stick to cutting edge. Mist down 3 times per day for three days.

---

### **Treatment Notes:**

Very unstable. Remove headstone off base. Chisel off old Portland cement mortar. Join headstone to base with stone epoxy lead wedges monument setting compound. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Robert Richardson

**Death Date:** 1898

**Location:** 437.16

**Marker Type:** Tablet stone and socket base

**Material:** Marble

**Condition:** Broken in base, reset in front of base

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.


---

### **Treatment Notes:**

Raise and re-level base. Chisel out broken tablet in base. Enlarge socket so tablet fits into base Reset into historic pointing mortar. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Sallie Mack

**Death Date:** 1923

**Location:** 908

**Marker Type:** Tablet stone on socket base

**Material:** Concrete

**Condition:** Leaning and biological growth

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Clean surfaces to be built up as described above. Infill lost stone with Jahn's Restoration Mortar, or St. Astier Lithomex. Follow the manufacturer guidelines for application. Pre-wet marker, apply a scratch coat, build up as needed. Cut down mortar once hardened enough to not stick to cutting edge. Mist down 3 times per day for three days.

---

### **Treatment Notes:**

Raise and re-level base. Infill corners of base and small crack at tablet. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Sarah Agnes Simons Brown

**Death Date:** Unknown

**Location:** 437.06

**Marker Type:** Small tablet stone

**Material:** Marble

**Condition:** Base missing

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Base missing. Construct new cast socket base. Reset in historic pointing mortar. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Sarah Stevenson

**Death Date:** 1908

**Location:** 949

**Marker Type:** Marble tablet stone with rails

**Material:** Marble

**Condition:** Missing base / rails broken

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Join the fragments of rails with Akemi, Akepox 2030. Immediately remove any adhesive which has spread to the outer surface of the marker.

### **Fills:**

Clean surfaces to be built up as described above. Infill lost stone with Jahn's Restoration Mortar, or St. Astier Lithomex. Follow the manufacturer guidelines for application. Pre-wet marker, apply a scratch coat, build up as needed. Cut down mortar once hardened enough to not stick to cutting edge. Mist down 3 times per day for three days.

---

### **Treatment Notes:**

Base missing. Cast replacement socket base at head of rails. Set tablet into socket base with historic pointing mortar. Join rails with stone epoxy on platform, infill. Lower section of rail missing. Create missing element with found marble in junk pile. Reconstruct bedstead up to tablet stone on sand and gravel base. Re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Simons family monument

**Death Date:** Not recorded

**Location:** Extra stone, not on list  
Center of Simons plot

**Marker Type:** Large pillar on two bases

**Material:** Marble

**Condition:** Sunken and not bonded to base

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.



---

### **Treatment Notes:**

Remove head stone from bases with lifting tripod. Raise and re-level bases with sand and gravel. Remove old bonding material. Lift back in place and join with stone epoxy on lead wedges with monument setting compound. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Susan Brown

**Death Date:** 1916

**Location:** Extra stone, not on list

**Marker Type:** Tablet stone in socket base

**Material:** Marble

**Condition:** Tablet fractured in two pieces

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Join the fragments with Akemi, Akepox 2030. Immediately remove any adhesive which has spread to the outer surface of the marker.

### **Fills:**

Clean surfaces to be built up as described above. Infill lost stone with Jahn's Restoration Mortar, or St. Astier Lithomex. Follow the manufacturer guidelines for application. Pre-wet marker, apply a scratch coat, build up as needed. Cut down mortar once hardened enough to not stick to cutting edge. Mist down 3 times per day for three days.

---

### **Treatment Notes:**

Raise and re-level base. Remove old repair material. Join fractured tablet with stone epoxy. Infill void areas. Reset in historic pointing mortar. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Susan M. Pearson

**Death Date:** 1893

**Location:** 418

**Marker Type:** Tablet stone in socket base

**Material:** Marble

**Condition:** Tablet fractured in two pieces

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Join the fragments with Akemi, Akepox 2030. Immediately remove any adhesive which has spread to the outer surface of the marker.

### **Fills:**

Clean surfaces to be built up as described above. Infill lost stone with Jahn's Restoration Mortar, or St. Astier Lithomex. Follow the manufacturer guidelines for application. Pre-wet marker, apply a scratch coat, build up as needed. Cut down mortar once hardened enough to not stick to cutting edge. Mist down 3 times per day for three days.

---

### **Treatment Notes:**

Fallen and buried face down. Only one edge of base and a small portion of tablet visible. Fractured at center of tablet and broken at key way. Chisel broken stone out of key way. Enlarge base to fit tablet. Raise and re-level base. Reset in historic pointing mortar. Join fractured tablet with stone epoxy. Infill large void areas. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Thomas Bacon

**Death Date:** 1923

**Location:** 905

**Marker Type:** Tablet stone in socket base

**Material:** Marble

**Condition:** Leaning and biological growth

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Realign and re-level base. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Tom Simons

**Death Date:** Unknown

**Location:** 437.07

**Marker Type:** Small tablet stone

**Material:** Marble

**Condition:** Base missing

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Base missing. Construct new cast socket base. Reset in historic pointing mortar. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Vencson Young

**Death Date:** 1900

**Location:** 467

**Marker Type:** Tablet stone in socket base

**Material:** Marble

**Condition:** Base fractured into multiple pieces  
and tablet fallen

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Join the fragments with Akemi, Akepox 2030. Immediately remove any adhesive which has spread to the outer surface of the marker.

### **Fills:**

Clean surfaces to be built up as described above. Infill lost stone with Jahn's Restoration Mortar, or St. Astier Lithomex. Follow the manufacturer guidelines for application. Pre-wet marker, apply a scratch coat, build up as needed. Cut down mortar once hardened enough to not stick to cutting edge. Mist down 3 times per day for three days.

---

### **Treatment Notes:**

Raise and re-level base. Join fractured base with stone epoxy. Infill large void areas on base. Reset tablet in historic pointing mortar. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interned:** Willie Wilkins

**Death Date:** 1928

**Location:** 930

**Marker Type:** Veterans tablet

**Material:** Marble

**Condition:** Fractured in two pieces

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Join the fragments with Akemi, Akepox 2030. Immediately remove any adhesive which has spread to the outer surface of the marker.

### **Fills:**

Clean surfaces to be built up as described above. Infill lost stone with Jahn's Restoration Mortar, or St. Astier Lithomex. Follow the manufacturer guidelines for application. Pre-wet marker, apply a scratch coat, build up as needed. Cut down mortar once hardened enough to not stick to cutting edge. Mist down 3 times per day for three days.

---

### **Treatment Notes:**

Tablet broken in two pieces. Lower portion embedded into tree roots. Excavate and cut free from tree. Cast new socket base approximately four feet from tree. Set into socket base with historic pointing mortar. Join fragments with stone epoxy, infill, re-grain and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.



---

**Interred:** Lucius Wimbush

**Death Date:** 1872

**Location:** 61.01

**Monument Type:** Obelisk on pedestal on  
two bases

**Material:** Marble

**Condition:** Leaning and misaligned /  
biological staining

---

### **Cleaning:**

Pre-treat the entire monument with D2 biological stone cleaner, applied to the stone when dry, to permeate deeply into the pores of the stone. This will kill off and destroy all biological activity and prevent its return for the foreseeable future. Hand -scrub the entire monument to detach biological activity while applying additional D2 stone cleaner, to free and remove lichens and molds. Rinse the entire monument completely to remove all loose materials and soiling.

### **Mends:**

Not required.

### **Fills:**

Not required.

---

### **Treatment Notes:**

Excavate and construct concrete footing under low side. Use hydraulic bottle jack to lift entire monument into level position. Realign into row. Fill all gaps between monumental elements with historic pointing mortar. Clean with D2, re-grade and seed.

### **Treatment Personal:**

All conservation procedures were performed by Jonathan Appell.

